



聚氨基酯 119

HCM 面漆 119 是一種單組水性防紫外光保護油
HCM 面漆 119 具有良好的遮蓋下部顏色。
非泛黃型不會變色。

特徵

1. 出色的附著力，可黏附 PU 的鋪層面。
2. 作為半光澤類型的頂部塗層，具有優異的耐用性。
3. 提供多程顏色滿足客戶需求。
4. 優異的防發黃，抗磨損性。
5. 優異的耐水性，耐久性，耐候性。
6. 出色的可操作性，隱蔽性。

使用方法

1. 暴露聚氨基酯防水劑的頂部塗層。
2. 使用 0.2-0.3 kg/m² 配合噴料器和滾筒一起使用。
3. 作為單組分水性面油，HCM 面漆 119 不需混合使用。
但是如果變成互相分離或沉澱，則必須加以混合使用。
4. 工作效率因溫度和濕度而異。

PU 119

HCM Top Coat 119 is a single component Water-base anti-UV resistance protective top coat.

HCM Top Coat 119 is good in concealment of lower part color.

This is not discoloration on non-yellowing type

Features

1. Excellent adhesion to based P/U layer paved.
2. Excellent durability as top coating of half-gloss coloring type.
3. Satisfy the demand of customer with variable colors.
4. Excellent non-yellowing, abrasion resistance, crashworthy
5. Excellent water-resistance, durability, Weatherability
6. Excellent workability, concealmentability

Instructions

1. Top coating of the exposure urethane waterproofing agents.
2. Use 0.2-0.3 kg/m² with spray and roller.
3. As a single component water-base top coating, HCM Top Coat 119 can use not mixing. But if it become phase separation or precipitation, it must mix
4. Work efficiency is a difference according to temperature and moisture.

Precautions

1. Use designated solvent (Water, Dimethylformamide), considering working condition. (0-5% to Resin)
2. Avoid the application above of relative humidity 80%, below atmospheric temperature 5°C

注意事项

1. 考慮工作條件，使用指定的溶劑（水、二甲基甲醯胺）。（0-5% 樹脂）
2. 避免應用於相對濕度 80% 以上，低於大氣溫度 5°C。
3. 應避免溫度高於 35°C，產品對冷凍敏感，不得儲存在低於 5°C 的溫度下。
4. 當它沾上衣服和皮膚時，可用肥皂水清洗。

效能

外觀：顏色液體

顏色：灰色。

拉伸強度 (%)：85

抗拉強度 (kgf/cm²) (ASTM 412)：76

抗撕裂強度 (kgf/cm²) (ASTM 624)：54.4

硬度 (Shore D) (ASTM 2240)：70-60

表面乾時間 (分鐘) 5-10°C: 40 以下

表面乾時間 (分鐘) 20-30°C: 20 以下

黏附力：非常好

耐久性：非常好

包裝

淨重

10 公斤

地址

H.C.M. 貿易公司

新界建旺街 4 號利通工業大廈 12 樓 3 室

WhatsApp: 9535 0688

Fax: 2399 0957

3. Temperature higher than 35°C should be avoided. The product is sensitive to the freezing and must not be stored at temperature below 5°C

4. When it is put on clothes and skin, wash with soap water.

Properties

Appearance: Colored Liquid

Elongation (%) (ASTM 412) : 85

Tensile strength (kgf/cm²) (ASTM 412) : 76

Tear resistant (kgf/cm²) (ASTM 624) : 54.4

Hardness (Shore D) (ASTM 2240) : 70-60

Tack Free Time (min) 5-10°C: 40 below

Tack Free Time (min) 20-30°C: 20 below

Adhesive Property: Excellent

Durability: Excellent

Package

Net weight

10 kg

Address

H.C.M. Trading Company

Flat 3, 12/F, Raton Industrial Building, 4 Kin Wong Street, Tuen Mun, N.T. Hong Kong